

Naftoseal[®] MC-460 Class A & B

FLOOR PANEL SEALANTS

1 Description

Naftoseal[®] MC-460 Class A & Class B are two-component, fast curing and flame-retardant sealants on base of Polysulfide with low density designed for sealing operations where good adhesion as well as removability of the seal for maintenance purposes is important.

The cured Naftoseal[®] MC-460 sealants are elastic and build up fast a good adhesion to the floor panels. Thus, these sealants are especially appropriate to fill gaps between floor panels with sandwich structure as used for aircraft construction.

At maintenance times the cured Naftoseal[®] MC-460 sealants can be removed easily by means of appropriate tools (like e.g. a plastic spatula) without harming the floor panels or even the supporting structure.

To allow optimum filling of different gap widths, Naftoseal[®] MC-460 sealants are available in two viscosity versions: Naftoseal[®] MC-460 Class A is pourable whereas Class B is paste-like.

Naftoseal[®] MC-460 sealants are available in Techkit 130 and can be mixed with the MCI Mixer and can be applied with a standard pneumatic sealant gun.

2 Applications

- Sealing of floor panels
- Sealing of parts which need to be removable e.g. for the purpose of maintenance

3

Application life and cure time at 23°C (73°F) / 50% r.H.			
Type	Min. Application Time	Tack-Free Time	Time to Shore A 20
Naftoseal [®] MC-460 A-1/4	15 minutes	≤ 3 hours	≤ 4 hours
Naftoseal [®] MC-460 B-1/4	15 minutes	≤ 3 hours	≤ 4 hours
Typical Physical and Application Properties			
	Base	Hardener	
Color	Beige	Brown	
Mixing ratio by weight	A 1/4: 100	7,5 +/- 15%	
	B 1/4: 100	7,5 +/- 15%	

Typical properties of cured compound

Colour	Brown
Specific gravity	≤ 1,15
Ultimate shore A hardness:	20 – 40
Service temperature	-55 °C (-67 °F) / +80 °C (+176 °F)

Mixing Instruction for Techkits

Naftoseal [®] MC-460 A-1/4 Naftoseal [®] MC-460 B-1/4	Motor revolution in rpm	Strokes up and down	Mixing Time
	110 ± 10	90	2 Min ± 1 Min

4 Surface preparation

To obtain good adhesion, clean surfaces with appropriate cleaners to remove dirt, grease and processing oils just prior to sealant application. Use lint-free rags or paper towels that are free of oil or soap. Always pour cleaner on the cloth to avoid contamination of the cleaner supply. Clean one small area at a time, quickly wiping it dry before the cleaner's solvent evaporates to prevent re-deposition of oil, wax or other contaminants.

5 Packaging

The material is supplied in Techkit 130 (137 ccm), with 24 Techkits per carton.

6 Storage

The shelf life of Naftoseal[®] MC-460 sealants is 4 months from date of manufacture, when stored at temperatures below 26 °C (+79 °F). Store in a dry place.

7 Health and safety precautions

See Safety Data Sheet.

The above details have been compiled to the best of our knowledge on the basis of tests and research work and with regard to the current state of our practical experience. This technical product information is non-binding. No liabilities or guarantees deriving from or in connection with this leaflet can be imputed to us. Statements relating to possible uses of the product do not constitute a guarantee that such uses are appropriate in a particular user's case or that such uses do not infringe the patents or proprietary rights of any third party. The reproduction of any or all of the information contained in this leaflet is expressly forbidden without Chemetall's prior written consent.

**Headquarters and Regional Head Office
Europe, Middle East, Africa, South America**
Chemetall GmbH
Trakehner Straße 3
60487 Frankfurt am Main, Germany
Tel: +49 (0) 69 7165-0

**Regional Head Office
North America**
Chemetall US, Inc.
675 Central Avenue
New Providence, NJ 07974, USA
Tel: +1-908-464-6900

**Regional Head Office
Asia-Pacific**
Chemetall Asia Pte Ltd.
12 Loyang Crescent
Singapur 508980
Tel: +65 6885 7900

www.chemetall.com | surfacetreatment@basf.com