

PU66 5462 8H NL Topcoat Matt

TECHNICAL DATA SHEET

Product Description

5462 is a two-component flexible polyurethane topcoat of the PU 66 range, designed for internal / external protection and decoration of aircraft structures.

- Conventional solids
- Excellent fluid resistance including skydrol hydraulic fluid
- Outstanding UV resistance & long term durability

Components



Mix Ratio (by volume)

- | | |
|-------------------------|--|
| • 5462/.... (Base) | 1 part |
| • 0730/9000 (Activator) | 1 part |
| • 0491/9000 (Thinner) | to viscosity (refer to viscosity section of this document) |

Specifications



5462 is qualified to:

- BLGG 140301
- MDL 5041

5462 meets the performance requirements of:

- MIL-PRF-85285

Product Compatibility

5462 is compatible with the following primer specifications:

- | | |
|------------------|-------------|
| • AIMS 04-04-002 | • RPS 661-2 |
| • BLGG 900101 | • S27-7004 |

Note: PPG Aerospace recommends you check the most recent specification QPLs for updated information

Surface Preparation and Pretreatment



Ensure surface is clean, dry and intact using a high performance solvent cleaner - DeSoto® CN20 or Desoclean™ 45 solvent cleaners are recommended. Observe recommended over coating window for primers. For further information, refer to technical data sheets for the relevant primers.

PU66 5462 8H NL Topcoat Matt

Instructions for Use



Base may require mechanical agitation. Ensure all components are adequately dispersed. Before adding the activator to the base, thoroughly stir or shake the base component until a smooth uniform mix is obtained. Slowly add activator to the base while stirring, then add required thinner while stirring.

Note: All products and components should be placed in ambient conditions of 15-30°C (59-86°F) for at least 24 hours prior to mixing and application.



Induction Time:


Not required



Viscosity: (21 - 25°C / 70 - 77°F)

• AFNOR2.5	45 - 55 seconds
• AFNOR4	14 - 16 seconds
• BSB3	23 - 30 seconds
• BSB4	18 - 20 seconds
• FORD4	13 - 15 seconds
• ISO3	30 - 50 seconds
• ISO4	17 - 22 seconds
• ZAHN2	15 - 20 seconds

Note: Viscosities quoted are typical ranges obtained when using specified mix ratio.



Pot Life:

4 hours @ 21 - 25°C (70 - 77°F)

Application Guidelines

Recommended Application Conditions:

Temperature	15 - 35°C (59 - 95°F)
Relative Humidity	30 - 85%

Application:

Apply 2 cross coats to achieve the recommended dry film thickness.




Theoretical Coverage: (ready for use unthinned)

6 - 8 m²/Lt @ 40 µm dry film thickness
240 - 320 ft²/US gal @ 1.6 mil dry film thickness

PU66 5462 8H NL Topcoat Matt

Recommended Dry Film Thickness:

30 - 50 µm
1.2 - 2 mil



Dry Film Density:

1.3 - 1.6 g/cm³ (depending on colour)
10.8 - 13.3 lbs/US gal

Dry Film Weight:

51 - 65 g/m² @ 40 µm dry film thickness
0.010 - 0.013 lbs/ft² @ 1.6 mil dry film thickness

Note: These application guidelines represent PPG's best advice for usage in standard conditions. Some parameters will be influenced by environmental conditions, equipment settings, and other variables.

Equipment:



Equipment Type	Tip Size (mm)	Pressure
HVLP Air Spray	1.2	22 to 29 psi (1.5 to 2 bar)
Pressure Pot	1.5	43 to 72 psi (3 to 5 bar)



Equipment Cleaning:

Clean spray equipment before use and as soon as possible after use. DeSoto[®] CN20, CN44 or Desoclean[™] 45 solvent cleaners are recommended.

Physical Properties



Colour:

This product is available in a wide range of colours. Please contact PPG Aerospace to discuss specific requirements.



Gloss:


≤ 5 units with a 60° gloss meter

PU66 5462 8H NL Topcoat Matt



DRYING TIMES @ 50 % R.H	23°C (73°F)	60°C (140°F)
Dust Free	2 hours	
Dry to Handle	5 hours	
Dry to Tape	8 hours	30 minutes
Dry to Overcoat	1 hour (min.) 72 hours (max.)	15 minutes
Full Cure	7 days	

Note: Drying times listed above are dependent upon film thickness applied, air flow conditions and application technique.



Flash Off Time:

15 - 30 minutes prior to force dry.



VOC: (ASTM)

Mixed ready for use	>600 g/Lt
5462 Base Component	460 g/Lt
0730/9000 Activator	705 g/Lt
0491/9000 Thinner	840 g/Lt



Flash Point:

5462 Base Component	2°C (61°F)
0730/9000 Activator	13°C (55°F)
0491/9000 Thinner	-2°C (28°F)

Shelf Life:

5462 Base Component	24 months in original unopened container
0730/9000 Activator	24 months in original unopened container
0491/9000 Thinner	10 years in original unopened container

Note: Shelf life may vary due to OEM specification requirements. Refer to container label for specific shelf life information.

Note: The application and performance property values above are typical for the material, but not intended for use in specifications or for acceptance inspection criteria because of variations in testing methods, conditions and configurations.

PU66 5462 8H NL Topcoat Matt

Storage Recommendations



Inspect the condition of the container to ensure compliance. The material should be stored at temperatures between 5°C to 35°C (41°F to 95°F) to ensure shelf life.

Note: When procuring to a qualified material specification, follow those storage instructions.



PU66 5462 8H NL Topcoat Matt

Health Precautions

This product is safe to use and apply when recommended precautions are followed. Before using this product, read and understand the Safety Data Sheet (SDS), which provides information on health, physical and environmental hazards, handling precautions and first aid recommendations. An SDS is available on request. Avoid overexposure. Obtain medical care in case of extreme overexposure.

For industrial use only. Keep away from children.

Additional information can be found at: www.ppgaerospace.com

For sales and ordering information call the local PPG office at the numbers listed below:

Asia Pacific

ASC – Australia

Tel 61 (3) 9335 1557
Fax 61 (3) 9335 3490

ASC – Japan

Tel 81 561 35 5200
Fax 81 561 35 5201

ASC – South East Asia

Tel 65 6861 1119
Fax 65 6861 6162

ASC – Suzhou

Tel (86-512) 6661 5858
Fax (86-512) 6661 6868

ASC – Tianjin

Tel (86-022) 2482 8625
Fax (86-022) 2482 8600

Americas

1 (818) 362-6711 or 1-800-AEROMIX

Europe and Middle East

ASC – Central Europe

Tel 49 (40) 742 193 10
Fax 49 (40) 742 139 69

ASC – Middle East & India

Tel (971) 4 883 9666
Fax (971) 4 883 9665

ASC – North Europe

Tel 44 (0) 1388 770222
Fax 44 (0) 1388 770288

ASC - South Europe

Tel 33 (0) 235 53 43 71
Fax 33 (0) 235 53 54 44

Desoclean, and DeSoto are trademarks of PRC-DeSoto International, Inc.

All recommendations, statements, and technical data contained herein are based on tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty, either expressed or implied. User shall rely on his own information and tests to determine suitability of the product for the intended use and assumes all risks and liability resulting from his use of the product. Seller's and manufacturer's sole responsibility shall be to replace that portion of the product of this manufacturer which proves to be defective. Neither seller nor manufacturer shall be liable to the buyer or any third person for any injury, loss, or damage directly or indirectly resulting from use of, or inability to use, the product. Recommendations or statements other than those contained in a written agreement signed by an officer of the manufacturer shall not be binding upon the manufacturer or seller.

PPG Aerospace
Sealants and Coatings
Darlington Road
Shildon, Co Durham UK
DL4 2QP

www.ppgaerospace.com

Issue Date: 06/18
Lit: 4204